

NYCO GREASE GN 15

TECHNICAL DATA SHEET

NATO CODE G-382

MINERAL AIRCRAFT GREASE

DESCRIPTION

Nyco Grease GN 15 is a lithium grease based on a mineral oil with a viscosity of 5 cSt at 100°C. It is inhibited against corrosion and oxidation and has good water resistance.

Nyco Grease GN 15 can be used from -40°C to +121°C.



APPLICATIONS

- Airframe multipurpose grease (doors, flaps, slaps, landing gear, etc.)
- Anti-friction bearings, plain bearings & gearboxes

SPECIFICATIONS * / **OEM's** & Airframers reference

- Approved DCSEA 382/A (ex AIR 4215)
- Meets MIL-G-7711 A (obs)
- Meets MIL-PRF-24139 B

- Listed in Airbus CML 03FBG1
- Listed in Airbus Helicopters CM150

^{*} Approved: The product has been approved by the relevant authority. The product is referenced on the applicable qualified product list.

Meets: The product complies with all the requirements of the specification and has not been formally approved or approval is in progress or the specification is obsolete.

| CHARACTERISTIC | UNIT | TYPICAL RESULT | DCSEA 382/A LIMIT | TEST METHOD |
|---|---------|------------------|------------------------------------|----------------------------|
| Appearance | - | pass | homogeneous smooth brown grease | visual |
| Dropping Point | °C | 193 | min. 170 | ASTM D566 |
| Worked Penetration after 60 strokes after 100 000 strokes change P100000/P60 | 1/10 mm | 274 315 31 | 265 to 295 - -5 to +45 | ASTM D217 FTM-S-791-313 |
| Oil Separation, 30 h at 100°C | % | 3.5 | max. 5.0 | ASTM D6184 |
| Evaporation Loss, 22 h at 100°C | % | 0.8 | max. 2.0 | ASTM D972 |
| Copper Corrosion, 24 h at 100°C | - | 1b | max. 1b | ASTM D4048 |
| Torque at -40°C (starting / 1h) | Nm | 0.8 / 0.04 | max. 1 / max. 0.1 | ASTM D1478 |
| Bearing Corrosion Test | - | pass | no corrosion | ASTM D1743 |
| Oxidation Stability at 100°C, after 100h / 400h | kPa | 7 / 28 | max. 35 / max 100 | ASTM D942 |
| Elastomer NBR-L Compatibility, 168h at 70°C | %v | 12 | max. 20 | ASTM D4289 |
| Water Washout at 38°C | %w | 2.3 | max 10 | ASTM D1264 |
| Apparent Viscosity at 0°C and 200s ⁻¹ | Ро | 140 | max 250 (MIL-PRF-24139 B) | ASTM D1092 |

The values above are typical values. They do not constitute any contractual commitment.

Sales specifications are available on request. The present technical data sheet replaces all the previous editions.

